

## *Plastiment® 200* Water Reducing and Set Retarding Concrete Admixture

**Description** A concrete plasticizer and retarder based on modified lignosulfonates used to produce good quality concrete.

Complies with ASTM C494 Type D

**Uses** Plastiment® 200 is used in structural and mass concrete where extended setting times and improved workability are required, such as projects with:

- Large pours, to prevent formation of cold joints
- Long travel times from the concrete plant to the site
- Difficult placing conditions and details
- High ambient temperature

**Advantages**

- Only set retarding, does not delay the hardening process.
- Allow substantial cement reduction compared to plain concrete
- Increase in ultimate strength
- Good control of slump loss even at elevated ambient temperature
- Reduced shrinkage and creep
- Chloride free, does not attack reinforcement steel
- Economical solution for low grade concrete

### Product Data

**Form/Colour** Liquid / Brown

**Packaging** 5 / 25 / 200 litres drum

**Storage** Dry, cool, shaded place.

**Shelf Life** Min. 1 year if stored properly in original unopened packaging

### Technical Data

**Base** Blend of Lignosulfonates / Carbohydrates

**Specific gravity** 1.155 - 1.180

**Chloride content** Nil



<b>Application</b>	
<b>Dosage</b>	0.20 – 0.6 ltr per 100 kg of cement (Depend on Cement type & brand)
<b>Typical dosage</b>	0.35 – 0.50 ltr. per 100 kg of cement
<b>Compatibility</b>	Possible to combine with all Sikament <sup>®</sup> , Sika <sup>®</sup> Aer, Sika <sup>®</sup> Pump, Sikacrete <sup>®</sup> PP1, but must be added separately to the mix and not pre-mixed prior addition.
<b>Cement types</b>	All Portland cement including sulfate resistant cement
<b>Dispensing</b>	Plastiment <sup>®</sup> 200 is either added to the gauging water prior to its addition to the dry concrete mix or added separately to wetted concrete mix, further mixing should take place for at least 1 minute per m <sup>3</sup> .
<b>Overdosing</b>	When overdosed, setting time will be extended, depending on cement content and temperature. Final strength will be not impaired.
<b>Note:</b>	<b><i>Due to extended setting time, proper curing must be ensured. Do not vibrate green concrete or tamper embedded rebars whilst setting.</i></b>
<b>Notes on application/ limits</b>	<ul style="list-style-type: none"> <li>■ Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. If assistance is required, please contact the Sika Technical Service Department.</li> <li>■ Accurate dispensing equipment can be supplied by Sika Ltd. Vietnam</li> <li>■ Use an appropriate mixer and do not mix by hand</li> <li>■ Curing treatment - use of Sika curing compounds to cure concrete is advisable</li> </ul>
<b>Health and Safety information</b>	
<b>Ecology</b>	Do not dispose into water
<b>Transportation class</b>	Non-hazardous
<b>Waste disposal</b>	According to local law
<b>Precautionary measures</b>	Avoid contact with foodstuffs and utensils. Avoid prolonged skin contact. In the event of contamination wash thoroughly with water. If the eyes or mouth are affected wash with clean water and obtain medical attention immediately.
<b>Disclaimer</b>	<i>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.</i>



Sika Limited (Vietnam)  
 Nhon Trach 1 Industrial Zone,  
 Nhon Trach Dist., Dong Nai Province  
 Tel: (84-61) 3560 700 Fax: (84-61) 3560 699  
 www.sika.com.vn, sikavietnam@vn.sika.com

