

Product Data Sheet
Edition 29/11/2017
Identification no: 0.0.000
Version no. 00
Plastiment® TM-28

Plastiment® TM-28

Water reducing and set retarding concrete admixture

Product Description	Plastiment® TM -28 is a water reducing and retarding concrete admixture, specially designed for roller compacted concrete (RCC). Plastiment® TM -28 meets the requirements of ASTM C 494 Type B & D.
Uses	Plastiment® TM-28 is used in structural and mass concrete where long setting times and improved workability are required, such as projects with: <ul style="list-style-type: none"> ■ Large pours, to prevent formation of cold joints in RCC dams etc ■ Long travel times from the concrete plant to the site ■ Difficult placing conditions and details ■ High ambient temperature
Characteristics / Advantages	<p>In fresh state</p> <ul style="list-style-type: none"> ■ Initial setting is delayed allowing time for proper placement and compacting new layer over the retarded RCC, without cold joint ■ Decrease the mortar of concrete bonding volume ■ Increase the time available to re compacting the concrete without damaging the material. After the initial set heavy transits can damage the newly hydrated RCC. ■ Increase of the cement efficiency ■ Diminish the rate of initial heat generation <p>In hardened state</p> <ul style="list-style-type: none"> ■ Increase the mechanical strengths in any weather conditions ■ Diminish the heat generation and the cracking risk ■ Increase the density of the RCC
Product Data	
Chemical Base	Blend of organic substances
Appearance/Colour	Liquid/ brownish colour
Packaging	200/1000 litres
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +30 °C
Shelf-life	12 months if stored properly in original unopened packaging
Density (at 20°C)	1.220 – 1.240 kg/l
pH Value (at 25°C)	6.00 – 8.00



Technical Data

Concreting Guidance	Concrete placing: With the use of Plastiment® TM-28, concrete of highest quality is being produced, however state of the art concrete technology, such as mixing, placing, vibrating and curing must be respected and applied Curing: Effective measures for concrete curing must be followed.
Special Advice	Plastiment® TM-28 is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix. For optimum utilization of the ultra-high range water reducer we recommend a minimum wet mixing time of 60 seconds. When adding the balance of the batching water to adjust concrete consistency this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.
Application	
Recommend Dosage	0.2 – 2 ltr per 100 kg of cement/binder Typical 0.4 – 2.0 ltr per 100kg of cement/binder
Compatibility	Plastiment® TM-28 may be combined with all Sikament, Sika® Aer, Sika® Pump, Sikacrete® PP-1 products, but must be added separately to the mix and not premixed prior its addition. Plastiment® TM-28 is compatible with all Portland Cement types.
Notes on application/ limits	Overdosing will result in increased workability and setting time of the Concrete, however, provided that curing is effective, ultimate concrete strength and properties will not be affected Accurate dispensing equipment can be supplied by Sika Limited (Vietnam). Use an appropriate concrete mixer and do not mix by hand. Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. Please contact Sika Technical Department for further assistance.
Basis of product data	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local restrictions	Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Protective measures	Avoid prolonged contact with skin. Wash off thoroughly with soap water. In case of contact with eyes or mouth, rinse immediately with clean warm water and seek medical attention without delay. Avoid contact with food stuff and utensils
Ecology/ Waste disposal	Do not dispose of into water or soil, but according to local regulations
Transportation class	Non-hazardous
Toxicity	Non-toxic
Disclaimer	<i>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.</i>

Construction



Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province
Tel: (84-251) 3560 700 Fax: (84-251) 3560 699
vnm.sika.com, sikavietnam@vn.sika.com

