

Sarnafil® G 476-12

Polymeric sheet for roof waterproofing

Description Sarnafil® G 476-12 (thickness 1.2 mm) is a multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) with inlay of glass non-woven .

Uses Waterproofing membrane for:

- Green roofs
- Ballasted roofs

Product Data

Visible defects	Pass	EN 1850-2
Length	25 (-0 / +5 %) m	EN 1848-2
Width	2 (-0.5 / +1 %) m	EN 1848-2
Straightness	≤ 30 mm	EN 1848-2
Flatness	≤ 10 mm	EN 1848-2
Effective thickness	1.2 (-5 / + 10 %) mm	EN 1849-2
Mass per unit area	1.6 (-5 / + 10 %) kg/m ²	EN 1849-2
Water tightness	Pass	EN 1928
Effects of liquid chemicals, including water	On request	EN 1847
Reaction to fire	E	EN ISO 11925-2 , classification after EN 13501-1
Joint shear resistance	≥ 500 N/50 mm	EN 12317-2
Water vapour transmission properties	μ = 15'000	EN 1931
Tensile strength,		EN 12311-2
longitudinal (md)*	≥ 9 N/50mm	
transversal (cmd)*	≥ 9 N/50mm	
Elongation,		EN 12311-2
longitudinal (md)*	≥ 180 %	
transversal (cmd)*	≥ 180 %	
Resistance to impact,		EN 12691
hard substrate	≥ 400 mm	
soft substrate	≥ 800 mm	

Construction



Resistance to static load,		EN 12730
soft substrate	≥ 20 kg	
rigid substrate	≥ 20 kg	
Dimension stability,		EN 1107-2
longitudinal (md)*	≤ 0.2 %	
transversal (cmd)*	≤ 0.1 %	
Foldability at low temperature	≤ -20 ^o C	EN 495-5
Resistance to root penetration	Pass	FLL
	*md = machine direction	
	*cmd = cross machine direction	

Disclaimer

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited (Vietnam)
 Nhon Trach 1 Industrial Zone,
 Nhon Trach Dist., Dong Nai Province
 Tel: (84-61) 3560 700 Fax: (84-61) 3560 699
 www.sika.com.vn, sikavietnam@vn.sika.com

