

## PRODUCT DATA SHEET

# SikaBond®-124 Instant Nails

### HIGH STRENGTH MULTIPURPOSE ADHESIVE

#### DESCRIPTION

SikaBond®-124 Instant Nails is a 1-part, rigid, construction adhesive with high final strength that bonds most common construction material substrate. Internal and covered external use.

#### USES

An adhesive to bond most construction components, such as:

- Skirting boards
- Wooden frames
- Ceramics, bricks
- Flooring panels
- Can be used on polystyrene and mirror
- Fibre-reinforced cement board
- Metal protection angles

#### CHARACTERISTICS / ADVANTAGES

- Easy to apply
- Rapid initial grab after flash off
- Rapid strength gain
- Wide adhesion range

#### PRODUCT INFORMATION

<b>Chemical base</b>	Synthetic rubber
<b>Packaging</b>	333 g cartridge, 12 cartridges per box
<b>Colour</b>	Wood Brown
<b>Shelf life</b>	18 months from the date of production
<b>Storage conditions</b>	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.
<b>Density</b>	~1,20 kg/l (ASTM D1002)

#### TECHNICAL INFORMATION

<b>Shore A Hardness</b>	~80 (after 28 d) (ISO 868)
<b>Shear Strength</b>	~3.2 N/mm <sup>2</sup> (ASTM D1002 Wood to Wood)
<b>Service temperature</b>	-30 °C min. / +60 °C max. (maximum 5 freeze / thaw cycles)

## APPLICATION INFORMATION

<b>Yield</b>	<b>1 Cartridge (333 g)</b>	<b>Dimension</b>
	~10 m bead	Nozzle diameter = 6 mm ~30 g per linear meter
	~100 spots	Diameter = 30 mm Thickness = 4 mm
<b>Ambient Air Temperature</b>	+5 °C min. / +40 °C max.	
<b>Substrate Temperature</b>	+5 °C min. / +40 °C max., min. 3 °C above dew point temperature	
<b>Open time</b>	~1-5 min (23 °C / 50 % r.h.)	

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATION

- For good workability, the adhesive temperature should be +20 °C
- Application during high temperature changes is not recommended (movement during curing).
- Before bonding, check adhesion and resistance of paints and coatings by carrying out a trial.
- **Sensitive application:**  
SikaBond®-124 Instant Nails contains solvents that might degrade and affect sensitive components and substrates (e.g. plastics). Before using on any of the below substrates, ensure compatibility by carrying out preliminary trials. Or contact Sika Technical Services:
  - + ) Overpainting
  - + ) Mirrors
  - + ) Natural Stone
  - + ) Plastics, such as, polyethylene (PE), polypropylene (PP), polytetrafluoroethylene (PTFE/ Teflon) and certain plasticised synthetic materials
- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation. Discolouration does not adversely affect the technical performance or durability of the product.
- Always use SikaBond®-124 Instant Nails in conjunction with mechanical fixings for overhead applications or heavy components.
- For very heavy components, provide temporary support until SikaBond®-124 Instant Nails has fully cured.
- Single Bond Method: Full surface applications / fixings are not recommended since the inner part of the adhesive layer may never cure.
- High levels of humidity or exposure to water can lead to adhesion failure.
- Excessive movement can lead to adhesion failure.
- **Limitations:**
  - + ) Do not use on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might leach oils, plasticisers or solvents that could degrade the adhesive.
  - + ) Do not use for bonding glass if the bond line is exposed to sunlight. Not suitable for outdoor use.

+ ) Do not use for structural bonding. Do not use for overhead mirror installations

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

All surfaces must be clean, sound, dry and free of oil, grease and surface contamination. Thoroughly remove all loose flaking particles and dust. Light abrasion is recommended for improved adhesion.

### APPLICATION METHOD / TOOLS

Any wet or partially wet adhesive can be removed with a piece of cloth. Dried adhesive is best removed with scraper or by sanding.

#### **One Way Method (Heavier substrate bonding)**

This method is recommended for heavier panels or where load or stress is expected. Apply a 4 to 6 mm bead of SikaBond®-124 Instant Nails using a cartridge gun, making sure the beads are no more than 50 mm apart. Bring both substrates immediately together and clamp, nail or screw for a minimum of 24 hours. For butt joints use adhesive on both panel edges.

#### **Two Way Method (Lighter substrate bonding)**

Apply adhesive as in one way method, bring together substrates, and press firmly over entire surface to transfer adhesive. Then pull apart. Allow adhesive to dry off up to 1 minutes (depending on ambient conditions) reposition the objects and press together with a hammer and a padded block to ensure maximum contact. Maximum bond strength will be achieved in 12 to 72 hours, depending on substrates and environmental conditions. Heavy panels may require temporary mechanical fastening until maximum strength is achieved.

## CLEANING OF TOOLS

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, hardened material can only be removed mechanically. For cleaning skin use Sika® Cleaning Wipes-100.

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,  
Nhon Trach Dist., Dong Nai Province,  
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



### Product Data Sheet

SikaBond®-124 Instant Nails

April 2021, Version 03.01

02051303000000100

SikaBond-124InstantNails-en-VN-(04-2021)-3-1.pdf