

**BUILDING TRUST** 

# PRODUCT DATA SHEET

# SikaPlast<sup>®</sup>-258 VN

# PCE BASED SUPERPLASTICIZING AND SET RETARDING CONCRETE ADMIXTURE.

# DESCRIPTION

SikaPlast<sup>®</sup>-258 VN is a 3rd generation polymer based high performance superplasticizer for producing soft consistency concrete.

SikaPlast<sup>®</sup>-258 VN meets the requirements of ASTM C 494 Type D & G.

SikaPlast<sup>®</sup>-258 VN conforms to Type G when used at 0.8 - 1.0% dosage, depending on cement type used.

# USES

SikaPlast<sup>®</sup>-258 VN is mainly suitable for the manufacture of concrete for RMC plants and site batch concrete.

SikaPlast®-258 VN is used for the following types of concrete:

- Bored piles.
- Barrette foundations and diaphragm walls.
- Ground and suspended slabs.
- Columns and walls.

# **CHARACTERISTICS / ADVANTAGES**

SikaPlast<sup>®</sup>-258 VN combines different modes of actions. By adsorption on the surface of the fines and keeping them apart while the hydration is in progress, SikaPlast<sup>®</sup>-258 VN effects the following concrete properties:

- Improve mortar phase when using coarse sand.
- Long slump keeping and high water reduction.
- High flowability (considerably reduced placing and compacting work).
- Faster evolution of early strength development.
- Workability can be maintained over 3 hours (still depends on admixture dosage, cement type, temperature).
- Improved creep and shrinkage resistance characteristics.
- When used at higher dosages, SikaPlast<sup>®</sup>-258 VN can give extended working time.

# **PRODUCT INFORMATION**

Chemical base	Modified Polycarboxylate in water.
Packaging	200/1000 litres.
Shelf life	12 months if stored properly in original unopened packaging.
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperat- ures between +5 °C and +30 °C.
Appearance / Colour	Liquid/brown colour.
Density	1.060 – 1.100 kg/L. (20ºC).

# **TECHNICAL INFORMATION**

#### **Concreting Guidance**

**Concrete placing:** With the use of SikaPlast<sup>®</sup>-258 VN, concrete of highest quality is being produced, however state of the art concrete technology, such as mixing, placing vibrating and curing must be respected and ap-

Product Data Sheet SikaPlast®-258 VN May 2024, Version 01.01 021301011000005546

### **APPLICATION INFORMATION**

Recommended Dosage	0.5 - 2 ltr per 100 kgs of cement/binder. Typical 0.8 to 1.2 ltr/100 kgs of cement/binder.
Compatibility	SikaPlast <sup>®</sup> -258 VN may be combined with all SikaPlast <sup>®</sup> , Sika <sup>®</sup> Aer, Sika <sup>®</sup> Pump, Sikacrete <sup>®</sup> PP1 products, but must be added separately to the mix and not pre-mixed prior its addition. SikaPlast <sup>®</sup> -258 VN is compatible with all Portland Cement types.

# **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# **IMPORTANT CONSIDERATION**

Overdosing will result in increased workability and setting time of the Concrete, however, provided that curing is effective, ultimate concrete strength and properties will not be affected.

Accurate dispensing equipment can be supplied by Sika Limited (Vietnam).

Use an appropriate concrete mixer and do not mix by hand.

Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. Please contact Sika Technical Department for further assistance.

# ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

# **APPLICATION INSTRUCTIONS**

#### DISPENSING

SikaPlast<sup>®</sup>-258 VN is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix.

For optimum utilization of the ultra-high range water reducer we recommend a minimum wet mixing time of 60 seconds.

When adding the balance of the batching water to adjust concrete consistency this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.

# LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

# LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam) Nhon Trach 1 Industrial Zone, Nhon Trach Dist., Dong Nai Province, Vietnam Tel: (84-251) 3560 700 Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



Product Data Sheet SikaPlast®-258 VN May 2024, Version 01.01 021301011000005546 SikaPlast-258VN-en-VN-(05-2024)-1-1.pdf



**BUILDING TRUST**