

PRODUCT DATA SHEET

Sikagard[®]-705 L

SILANE BASED REACTIVE WATER REPELLENT IMPREGNATION

DESCRIPTION

Sikagard[®]-705 L is a one-component low viscosity, solvent free, reactive impregnation for concrete and cementitious substrates based on silane with 99% active ingredient. Sikagard[®]-705 L complies with the highest requirements of EN 1504-2 for hydrophobic Impregnation (penetration depth class II & resistance to freeze and thaw salt stresses).

USES

Sikagard[®]-705 L is used as water-repellent impregnation (hydrophobic treatment) for absorbent substrates such as concrete in civil engineering or building concrete structures subjected to heavy stress due to freeze and thaw cycles and de-icing salts and chloride attack in marine environment, etc...

- Suitable for protection against ingress (Principle 1, method 1.1 of EN 1504-9)
- Suitable for moisture control (Principle 2, method 2.1 of EN 1504-9)
- Suitable for increasing the resistivity (Principle 8, method 8.1 of EN 1504-9)

CHARACTERISTICS / ADVANTAGES

- Excellent penetration (~100% active content)
- Economic and easy to use
- Reduces capillary water absorption, protection against driving rain and splashing on vertical areas
- Reduction of absorption of aggressive or deleterious agents dissolved in water (i.e. de-icing salts or chloride from marine environment)
- No change in water vapour permeability
- Long term efficiency, deep penetration
- Increases the resistance of concrete to freeze and thaw cycles and de-icing salts
- Resistant to sea water
- Low VOC content
- Ready to use

APPROVALS / STANDARDS

- Conforms to the requirements of LPM: Suitability test to SIA 162/5, Report No. 1-21'699-6.
- Conforms to the requirement of the "Bro 2002" Swedish National Road Administration (SNRA) publication No. VV2002:47 Report ref: F507580 B rev.
- Evaluation of Conformity According to the Dutch RWS Directive (11-01-2011) and the European Standard EN 1504-2 – Sika MPL; test report no. 1203052 dated 09.04.2012.
- Conforms to the requirements of the EN 1504-2 class II – Polymer Institute report P 5634-E dated 5th April 2007.
- Active content - Polymer Institute Ref P5634-E dated 27th June 2008.

PRODUCT INFORMATION

Chemical base	Silane (99% active ingredient)
Packaging	18 kg pail and 170 kg drum
Appearance / Colour	Water like liquid, colourless

Shelf life	12 months from date of production	
Storage conditions	Stored in unopened, undamaged and original sealed packaging in dry and cool conditions. Protect from moisture.	
Density	~ 0.900 kg/l (at +25 °C)	
Volatile organic compound (VOC) content	~100 g/l (~1% w/w)	
Viscosity	~9 mm ² /s (at 25 °C)	
Water Absorption	<7.5%	(EN 13580)

TECHNICAL INFORMATION

Resistance to Alkalinity	< 10%	(EN 13580)
Freeze Thaw De-icing Salt Resistance	Comply	(EN 13581)
Penetration Depth	Class II: ≥ 10 mm	Test performed on concrete with a W/C = 0.70
Drying Rate Coefficient	Class I: > 30%	(EN 13579)

SYSTEM INFORMATION

System Structure	2–3 coats applied "wet on wet"
-------------------------	--------------------------------

APPLICATION INFORMATION

Consumption	Dependent on absorbency of the substrate as well as the required penetration depth: ~ 150 g/m ² per coat.
Ambient Air Temperature	+5 °C min. / +40 °C max.
Substrate Temperature	+5 °C min. / +35 °C max.
Waiting Time / Overcoating	Can be overcoated with water and solvent based polymer paint - contact the proposed paint manufacturer for recommendations. Sikagard®-705 L can be used as a water repellent primer under many Sikagard® protective coatings. Penetration of water is thus prevented at possible weak spots or in the event of damage to the top coat and the risk of consequential damages such as paint flaking can be reduced. Waiting time: minimum 5 hours, maximum 1 week.

CURING TREATMENT	Sikagard®-705 L does not require any special curing but must be protected from rain for at least 3 hours at +20 °C.
-------------------------	---

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Substrate Quality

Free of dust, dirt, oil, efflorescence and existing paint coatings.

Cracks in concrete more than 300 microns must be repaired first prior to carry out the hydrophobic treatment.

Substrate Preparation

Cleaning is best done with suitable detergents or by light blastcleaning, steam cleaning etc.

Best results are obtained on dry, very absorbent substrates. The substrate must look dry with no damp patches.

MIXING

Sikagard®-705 L is supplied ready for use and must not be diluted.

APPLICATION

Sikagard®-705 L is applied using a low-pressure spray, brush or roller, in a single pass from bottom up taking care not to let the product run. Apply subsequent coats wet on wet. Avoid ponding on the surface.

CLEANING OF TOOLS

Clean all tools and application equipment with Colma cleaner immediately after use. Hardened / cured material can only be mechanically removed.

IMPORTANT CONSIDERATION

Best results are achieved when Sikagard®-705 L is applied on 28 days old concrete – however, due to its high alkali resistance, it is still possible to apply it at a very early age.

Areas such as window frames which still need to be painted must be securely covered to avoid contact with Sikagard®-705 L.

Areas not to be impregnated such as window panes need to be protected from being accidentally contaminated with Sikagard®-705 L.

Sikagard®-705 L can damage some coatings and bituminous products.

Sikagard®-705 L can lead to darkening of concrete, apply sample areas first.

Cannot be overcoated with limewash or cement paint.

Refer to the latest Method Statement for detailed information regarding surface preparation, application method, etc.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Tel: (84-251) 3560 700
Fax: (84-251) 3560 699
sikavietnam@vn.sika.com
vnm.sika.com



Product Data Sheet
Sikagard®-705 L
November 2017, Version 03.01
020303010010000004

Sikagard-705L-en-VN-(11-2017)-3-1.pdf