

PRODUCT DATA SHEET

SikaGrind®-874 VN

EFFICIENT GRINDING AID AND PERFORMANCE ENHANCER FOR THE CEMENT

DESCRIPTION

SikaGrind®-874 VN is liquid cement grinding aid with performance enhancing properties. SikaGrind®-874 VN has been specifically designed to increase the output of cement grinding plants and obtain improved strength development for cements with high amount of clinker replacements

USES

- Improve the production rate of the cement grinding system.
- Increase the strength of the cement.

CHARACTERISTICS / ADVANTAGES

SikaGrind®-874 VN is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of the cement particles
- Separation of the cement particles

SikaGrind®-874 VN provides the following advantages in the cement production:

- Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners
- Higher separator efficiency due to improved cement particle dispersion
- Reduced relative power consumption per ton of cement due to increased output of the grinding system (tons per hour)
- Easier achievement of the desired cement fineness (Blaine, particle fraction > 32µm, granulometry) due to reduced re-agglomeration of the sufficiently ground cement particles
- Minimized problems with “plugging” due to improved powder flow characteristics

SikaGrind®-874 VN gives the following advantages to the finished cement:

- Reduced quantity of “over-milled” particles in the cement granulometry
- Easier discharge of the silos
- Increased strengths
- Economic cement design with clinker replacements

PRODUCT INFORMATION

Chemical base	Aqueous polymers solution
Packaging	1000 kg IBC Bulk deliveries
Appearance / Colour	Brown liquid
Shelf life	12 months if stored properly in original unopened packaging
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +35 °C Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.
Density	1.040 – 1.120 kg/L (at 20°C)

APPLICATION INFORMATION

Recommended Dosage	Typical dosage rates of SikaGrind®-874 VN are between 0.2–0.7 kg per tonne of cement (0.02 %–0.07 % of total weight = cement clinker + additions). The optimum dosage to achieve the desired characteristics shall be determined in Plant trials. Influencing factors are e.g. the properties of clinker source, type of cement and other plant variables. For consistent results, SikaGrind®-874 VN must be accurately dispensed
Compatibility	Cements treated with SikaGrind®-874 VN are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-874 VN

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DISPENSING

SikaGrind®-874 VN is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing.

Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam
Tel: (84-251) 3560 700
Fax: (84-251) 3560 699
sikavietnam@vn.sika.com



Product Data Sheet
SikaGrind®-874 VN
August 2021, Version 02.02
021407021000000324

SikaGrind-874VN-en-VN-(08-2021)-2-2.pdf