

(ASTM D412)

# PRODUCT DATA SHEET

# Sikalastic®-110

### HIGH ELASTICITY, ONE PART POLYURETHANE MODIFIED WATERPROOFING COATING

#### **DESCRIPTION**

Sikalastic®-110 is a water based one part modified polyurethane coating, formulated to form a highly elastic, seamless and crack bridging membrane.

#### **USES**

Due to its high elasticity, Sikalastic®-110 can be applied on different structures including those subject to thermal movement and vibration such as:

- Concealed RC roof
- External walls to be buried below ground like retaining walls, basements, foundations, etc.
- Waterproofing coating under tiles, plaster or screeds areas such as podium, balconies, planter box, etc.

# **CHARACTERISTICS / ADVANTAGES**

- Easy to apply by roller, brush or airless spraying
- High elasticity
- High crack bridging capability
- Optimum adhesion onto concrete
- Can be applied directly on damp surface
- Non-toxic
- Low VOC and Eco-friendly

#### **SUSTAINABILITY**

Singapore Green Label Certifiate

#### PRODUCT INFORMATION

Chemical base	Polyurethane bituminous hybrid	
Packaging	20 kg pail	
Colour	Black	
Shelf life	9 months from date of production if stored properly in undamaged and unopened original sealed packaging.	
Storage conditions	Store in undamaged original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +5 °C and +30 °C	
Density	1.08 kg/l	
TECHNICAL INFORMATION		
Tensile Strength	~1.0 N/mm² (Without reinforcement, at 14 days, +25 °C) (ASTM D412)	

> 600 % (Without reinforcement, at 14 days, +25 °C)

Product Data Sheet Sikalastic®-110 September 2019, Version 02.02 020915255000000002

**Elongation at Break** 

#### SYSTEM INFORMATION

System Structure	Standard Coating System	
	Primer	1 x dilute 1 part Sikalastic®-110 at ~0.2 kg/m² with 1 part of clean water
	Coating	Min. 2 x Sikalastic®-110 at ~0.65 kg/m²/coat
	Total Consumption	~1.5 kg/m²
	Reinforced Coating System	
	Primer	1 x dilute 1 part Sikalastic®-110 at ~0.2 kg/m² with 1 part of clean water
	Coating	1 x Sikalastic®-110 at ~0.8 kg/m² + Sika Reemat Premium reinforcement + 2 x Sikalastic®-110 at ~0.5 kg/m²
	Total consumption	~2.0 kg/m²

# **APPLICATION INFORMATION**

Ambient Air Temperature	+5 °C min. / +40 °C max.
Relative Air Humidity	Max. 80 % r.h.
Substrate Temperature	+5 °C min. / +40 °C max.
Waiting Time / Overcoating	First coat can be applied immediately after the primer become tacky free. Allow minimum 4 - 5 hours (at +25 °C) between the first coat and second coats.
Applied Product Ready for Use	Sikalastic®-110 should be allowed to cure for min. 48 - 72 hours (at +25 °C) prior to overlaying with screed.  Before ponding test (if required), allow Sikalastic®-110 to cure at least 5 - 7 days (at +25 °C).

#### **APPLICATION INSTRUCTIONS**

#### **SUBSTRATE PREPARATION**

The concrete must be dry, structurally sound, laitance free, clean and free from dirt, oil, grease or other contaminants and loose or friable particles. The substrate must be sound and of sufficient strength. If in doubt, apply a test area first.

Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed. All dust, loose and friable material must be completely removed from all surface before application of the product, preferably by brush and/or vacuum. The substrate should be well dampened but free of surface water and leaks.

#### **MIXING**

Prior to application stir Sikalastic®-110 thoroughly in order to achieve a homogeneous mix

#### **APPLICATION**

Sikalastic®-110 is applied using brush, roller or by spraying machine.

#### **CLEANING OF TOOLS**

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be mechanically removed.

#### IMPORTANT CONSIDERATION

- Do not add extra water or other ingredients (except for priming layer, where only clean water is added)
- Sikalastic®-110 may cure slower when the relative humidity is high, i.e. in closed or inadequately ventilated rooms and basements
- Do not allow temporary ponding to remain between coats on any horizontal surfaces or until the final coating has totally cured. Brush or mop surface water away during this time
- Freshly applied Sikalastic®-110 should be protected from rain for at least 8 hours (at +25°C)
- Do not allow permanent exposed under UV

#### **BASIS OF PRODUCT DATA**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

#### LOCAL RESTRICTIONS

Please note that as a result of specific local regula-

Product Data Sheet Sikalastic®-110 September 2019, Version 02.02 020915255000000002



tions the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

# **ECOLOGY, HEALTH AND SAFETY**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone, Nhon Trach Dist., Dong Nai Province, Tel: (84-251) 3560 700 Fax: (84-251) 3560 699 sikavietnam@vn.sika.com vnm.sika.com





Product Data Sheet
Sikalastic®-110
September 2019, Version 02.02
020915255000000002

Sikalastic-110-en-VN-(09-2019)-2-2.pdf

