

PRODUCT DATA SHEET

SikaGrind®-737

EFFICIENT GRINDING AID FOR THE PRODUCTION OF CEMENT

DESCRIPTION

SikaGrind®-737 is a chloride-free liquid cement grinding aid with performance enhancing properties. SikaGrind®-737 has been specifically designed to increase the output of cement grinding plants and obtain improved strength development for cements with high amount of clinker replacements.

USES

- Improve the production rate of the cement grinding system;
- Increase the early strength of the cement.

CHARACTERISTICS / ADVANTAGES

SikaGrind®-737 is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of the cement particles;
- Separation of the cement particles.

SikaGrind®-737 provides the following advantages in the cement production:

- Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners.

- Higher separator efficiency due to improved cement particle dispersion;
- Reduced relative power consumption per ton of cement due to increased output of the grinding system (tons per hour);
- Easier achievement of the desired cement fineness (Blaine, particle fraction > 32µm, granulometry) due to reduced re-agglomeration of the sufficiently ground cement particles;
- Minimized problems with “plugging” due to improved powder flow characteristics;

SikaGrind®-737 gives the following advantages to the finished cement:

- Reduced quantity of “over-milled” particles in the cement granulometry;
- Easier discharge of the silos;
- Increased strengths;
- Economic cement design with clinker replacements.

APPROVALS / STANDARDS

SikaGrind®-737 is produced under quality management systems according to EN ISO 9001.

PRODUCT INFORMATION

Chemical base	Aqueous polymers solution
Packaging	1000 kg IBC Bulk deliveries
Appearance / Colour	Clear brownish liquid
Shelf life	At least 12 months in undamaged, unopened and sealed original containers when stored at temperatures between +5 °C and +35 °C.

Storage conditions	Protect from frost, direct sunlight and contamination. <u>Note:</u> When delivered in bulk, the tanks and equipment used must be free from contaminants.
Density	1.09 ± 0.02 kg/l (at +20 °C)
pH-Value	7.00–9.50 (at 25 °C)

APPLICATION INFORMATION

Recommended Dosage	Typical dosage rates of SikaGrind®-737 are between 0.2–0.7 kg per tonne of cement (0.02 %–0.07 % of total weight = cement clinker + additions). The optimum dosage to achieve the desired characteristics shall be determined in Plant trials. Influencing factors are e.g. the properties of clinker source, type of cement and other plant variables. For consistent results, SikaGrind®-737 must be accurately dispensed.
Compatibility	Cements treated with SikaGrind®-737 are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-737.
DISPENSING	SikaGrind®-737 is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. <u>Note:</u> Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)
 Nhon Trach 1 Industrial Zone,
 Nhon Trach Dist., Dong Nai Province,
 Tel: (84-251) 3560 700
 Fax: (84-251) 3560 699
 sikavietnam@vn.sika.com
 vnm.sika.com



Product Data Sheet
 SikaGrind®-737
 July 2017, Version 01.01
 021407021000000459

SikaGrind-737-en-VN-(07-2017)-1-1.pdf