

PRODUCT DATA SHEET

SikaFiber®-8060 HE

STEEL FIBRES FOR REINFORCEMENT OF CONCRETE

DESCRIPTION

SikaFiber®-8060 HE are filaments of wire, deformed and cut into length, for reinforcement of concrete. They are collated by water soluble glue and with hooked ends.
SikaFiber®-8060 HE complies with ASTM A820.

USES

SikaFiber®-8060 HE are used as reinforcements of:

- Flooring reinforcements
- Precast reinforcements
- Bridge

CHARACTERISTICS / ADVANTAGES

- Increased crack resistance, ductility, energy absorption and toughness of concrete
- Improve impact resistance, fatigue endurance and shear strength of concrete
- High tensile strength fiber bridging joints to increase load-carrying capacity
- Require less labor to incorporate into concrete than conventional reinforcement
- Minimize maintenance and repair expense

PRODUCT INFORMATION

Chemical base	Low carbon steel
Packaging	20 kg normal bags or 1,000 kg bags
Appearance / Colour	Cold drawn wire
Shelf life	12 months if stored properly in original unopened packaging
Storage conditions	Store in dry conditions at temperatures between +5°C and +30°C. Do not stack the pallets on each other.
Density	7.85 kg/m ³
Dimensions	Length (l): 60 mm Diameter (d): 0.75 mm Aspect ratio (l/d): 80

TECHNICAL INFORMATION

Tensile Strength	1,250 MPa
------------------	-----------

APPLICATION INFORMATION

Recommended Dosage	20-40 kg/cubic meter of concrete
--------------------	----------------------------------

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATION

It is always advisable to carry out trial mixes to establish the exact dosage required.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

DISPENSING

Preferably produce the Steel Fiber Reinforced Concrete in a central batching plant mixer.

Never add the fibers as the first material in the mixer!

Fibers can be added together with the aggregate or directly into freshly mixed concrete.

Mixing time is not increased significantly with the addition of fibers. Mixing must proceed until all glued fibers are separated individually.

Drum mixer

Open bag and add fiber directly into the mixer.

Truck mixer

Run the mixer drum at a speed of 12 – 18 rpm. Adjust the slump to a minimum of 12 cm, depending on the actual fiber dosage. Preferably use a water reducing or high range water reducing admixture. Add the fibers in a maximum ratio of 40 kg/min. After adding the fibers, continue mixing at full speed 1 minute/m³ of concrete and not less than 5 min.

Fiber Concentration: approx. 4,800 fibers/kg

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



Product Data Sheet

SikaFiber®-8060 HE

June 2022, Version 02.01

021408011000000103

SikaFiber-8060HE-en-VN-(06-2022)-2-1.pdf