

PRODUCT DATA SHEET

Sikafloor[®]-2 SynTop 1 VN

COLOURED NON-RUSTING ALLOY AGGREGATES DRY SHAKE FLOOR HARDENER

DESCRIPTION

Sikafloor[®]-2 SynTop 1 VN is one part, preblended, coloured synthetic dry hardener for concrete comprising of cement, hard aggregates, compatible admixtures and pigments.

USES

Sikafloor[®]-2 SynTop 1 VN may only be used by experienced professionals.

- Sikafloor[®]-2 SynTop 1 VN provides a hard wearing, dry shake topping for monolithic floors. When sprinkled any trowelled into fresh wet concrete floors, it forms a wear resistant smooth surface.
- Typical users are in warehouses, distribution centers, factories, industrial facilities, aircraft hangars, DIY stores, supermarkets, shopping malls, offices and museums.

CHARACTERISTICS / ADVANTAGES

- Very high wear resistance rating
- Good impact resistance
- Cost effective, long life floor
- Maintenance free
- Slip resistant surface possible
- Dust proof
- Increased resistance to oils and grease
- Available in colours

PRODUCT INFORMATION

Chemical base	Blend of natural and synthetic aggregates mixed with cement, admixtures and pigments.	
Packaging	25 kg bag	
Appearance / Colour	Powder Natural (concrete grey) Other colours upon request.	
Shelf life	6 months from date of production	
Storage conditions	Store in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 to +30.	
Density	~ 2.0 ± 0.1 kg/l	
Abrasion Resistance	II≥350%	(JC/T906)
	Note: Abrasion Resistance Ratio	

SYSTEM INFORMATION

System Structure

Substrate
Dry shake

Fresh concrete slab
Sikafloor®-2 SynTop 1 VN

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATION

- The application of Sikafloor®-2 SynTop 1 VN must not be carried out in strong wind or in dry conditions.
- Sikafloor®-931 Finishing Aid is strongly recommended to use together with dry shake, especially in hot season;
- Do not use concrete where some cement has been replaced by fly ash, as this makes the mix sticky and less workable.
- Variations in concrete characteristics such as water content and cement may lead to slight colour variations.
- Dry shake hardeners give a finish to concrete with some colour variation across the floor due to the natural variability of the concrete onto which they are applied.
- To ensure optimum of colour consistency, it is essential that the floor laying operation is as clean and protected from the environment as possible.
- Colour variation during the drying out period is normal for this system and is to be expected.
- Every effort must be made to ensure an even application of Sikafloor®-2 SynTop 1 VN. Correct timing and trowelling techniques are essential.
- At low relative humidity (below 40 %), efflorescence can appear on the surface.
- At high relative humidity (above 80 %), bleeding, slower curing and hardening can occur and extended finishing operations be required.
- Slip resistance can be enhanced through chemical ageing.
- Refer to the Method Statement for Application for details.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The concrete deliveries must be of consistent quality and comply with local standards. Concrete characteristics are specified by its class determined in the static design and by general recommendations for concrete mix design. W/c- ratio must not be too low as some water is required for hydration of the Sikafloor®-2 SynTop 1 VN. Generally recommended w/c- ratios are between 0.45 to 0.55 and must be consistent while being poured. The compressive strength must be a minimum of 25 N/mm².

Use of Sikament® or Sika Viscocrete® super plasticisers is advised to ensure the optimum dispersion within the mix.

Air entrained concrete is not a suitable substrate for the application of dry shake hardeners.

APPLICATION

Mechanical Application - Automatic spreader in conjunction with a laser screed

Spread Sikafloor®-2 SynTop 1 VN evenly onto the concrete immediately after screeding at ~5 kg/m² in one application.

Manual application

Dependent on the conditions, remove the surface bleed water or allow it to evaporate. Sprinkle Sikafloor®-2 SynTop 1 VN onto the screeded concrete evenly in 2 stages (first stage: 3 kg/m²; second stage: 2 kg/m²).

Care must be taken to apply the product without creating ripples etc. in the concrete surface. Casting Sikafloor®-2 SynTop 1 VN powder carelessly or further than 2 metres from point of casting will reduce the consistency of finish.

Compaction: The first application must be worked into the slab followed immediately by the application of the second stage quantity of Sikafloor®-2 SynTop 1 VN.

Notes:

- Never add water to the surface where the dry shake has been applied, it is recommended to use Sikafloor®-931 Finishing Aid to improve the workability.
- Sikafloor®-2 SynTop 1 VN results in the slab surface becoming stiff more quickly than usual.
- Careful trimming must take place along the edges where adjoining slabs are to be poured.
- Final finishing for closing pores and removing undulations can be achieved either by hand or powered trowel.

Application time

Application time for dry shake products is influenced by every variable which affects the placing of concrete, and can therefore vary substantially, depending on the prevailing conditions, especially when using Sika-

floor®-931 Finishing Aid.

For mechanical application with automatic spreader and laser screed, the spreading can start almost immediately after the concrete has been levelled to allow for the hydration of the dry shake. Compaction with the trowel can start as soon as the weight of the power trowels is supported by the concrete.

For manual application, the dry shake must be spread once the concrete can be stepped on, without leaving a print deeper than 3-5 mm.

Periodical checking of the condition and development of the concrete will determine the correct time frame for each stage and sequence of application.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users can always refer to the most recent version of the local Product Data Sheet for relevant product, available on our website. The information in any downloaded version is valid as of the time of download.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



Product Data Sheet

Sikafloor®-2 SynTop 1 VN

January 2026, Version 01.01

020815010020247768

Sikafloor-2SynTop1VN-en-VN-(01-2026)-1-1.pdf