

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-24

Broadcast unicolour epoxy floor covering with high mechanical resistance

DESCRIPTION

Sikafloor® MultiDur EB-24 is a slip resistant, coloured, epoxy covering with high mechanical resistance for flooring applications

USES

Sikafloor® MultiDur EB-24 may only be used by experienced professionals.

- for concrete and cement screeds with normal up to medium heavy wear e.g. storage and assembly halls, maintenance workshops, garages and loading ramps.
- for multi-storey and underground car parks and for wet process areas, e.g. beverage and food industry

CHARACTERISTICS / ADVANTAGES

- High wear resistance
- High mechanical resistance
- Good chemical resistance
- Easy application
- Waterproof
- Gloss finish
- Slip resistant

APPROVALS / STANDARDS

 Fire classification test, Bfl-S1 according to DIN EN 13501-1, Report No.2007-B-0181/15, Germany, July 2007

PRODUCT INFORMATION

Packaging	Please refer to the individual	Please refer to the individual Product Data Sheet			
Shelf life	Please refer to the individual	Please refer to the individual Product Data Sheet			
Storage conditions	Please refer to the individual	Please refer to the individual Product Data Sheet			
TECHNICAL INFORMAT	ION				
Reaction to Fire	Bfl-S1		(DIN EN 13501-1)		
CHEMICAL RESISTANCE	Refer to the chemical resistan	Refer to the chemical resistance of Sikafloor®-264			
Thermal Resistance	Exposure*	Dry heat			
	Permanent	+50 °C			
	Short-term max. 7 d	+80 °C			
	Short-term max. 12 h	+100 °C			
	Short-term moist/wet heat* up to +80 °C where exposure is only occasional (i.e. during steam cleaning etc.) *No simultaneous chemical and mechanical exposure.				
Skid / Slip Resistance	35 BPN wet condition (Quartz Sand 0.3 - 0.7 mm)		(ASTM E303)		
	50 BPN wet condition (Quartz Sand 0.7 - 1.7 mm)		(ASTM E303)		

SYSTEM DATA SHEET

Sikafloor® MultiDur EB-24October 2024, Version 04.01
020811900000000017

SYSTEM INFORMATION


System Structure

Chemical base

Nominal Thickness

Appearance

Colour



Sikafloor® MultiDur EB-24 system (~ 2–4 mm)

	1. Primer	Sikafloor®-156/-161/-160
	2. Wearing coat & broadcast in ex-	Sikafloor®-263 SL or
	cess	Sikafloor®-264
		broadcast with quartz sand in excess
	3. Top coat	Sikafloor®-264
	Ероху	
	Slip resistant, gloss finish	
-		

APPLICATION INFORMATION

Consumption	Sikafloor® MultiDur EB-24 system (~ 2–4mm)				
	Coating System	Product	Consumption		
	Primer	1 x Sikafloor®-156 /- 160/-161	~ 0.3–0.5 kg/m ² ~ 4 kg /m ² (2 kg/m ² binder + 2 kg/m ² quartz sand)		
	Wearing coat	Sikafloor®-263 SL or Sikafloor®-264 filled 1:1 with quartz sand 0.1–0.3mm			
	Broadcast in excess	quartz sand 0.3 – 0.7 mm	~ 4–6 kg/m²		
	Top coat	1–2 × Sikafloor®-264	~0.6–0.8 kg/m²		
Product Temperature	Please refer to the inc	lividual Product Data Shee	t		
Ambient Air Temperature	+10 °C min. / +30 °C m	ıax.			
Relative Air Humidity	80 % r.h. max.				
Dew Point		on! cured floor must be at leas densation or blooming on	•		
Substrate Temperature	+10 °C min. / +30 °C m	nax.			
Substrate Moisture Content	substrate moisture co Tramex.	olication work with Sikafloo ntent must not exceed 4 % ramex meter, CM - measur			

Available in various colour shades.

~2.0-4.0 mm

SYSTEM DATA SHEET
Sikafloor® MultiDur EB-24
October 2024, Version 04.01
020811900000000017



	No fishing moisture according to Ashivi (i divernivene-sheet).											
Waiting Time / Overcoating	Before applying Sikafloor®-263 SL/-264 on Sikafloor®-156/161/160 allow											
	Substrate temperature +10 °C +20 °C +30 °C		Minimum 24 hours 12 hours 8 hours		Maximum 3 days 2 days 1 day							
							Before applying Sikafloor®-264 on Sikafloor®-263 SL/-264 allow:					
							Substrate tempe	erature	Minimum		Max	imum
							+10 °C +20 °C +30 °C		30 hours 24 hours 16 hours		48 hours 24 hours 30 hours	
	Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity											
	Applied Product Ready for Use	Temperature	Foot	traffic	Light traffic							
		+10 °C	~ 72	hours	~ 6 days		~ 10 days					
		+20 °C	~ 24	hours	~ 4 days		~ 7 days					
		+30 °C	~ 18	hours	~ 2 days		~ 5 days					
							- ·					

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Please refer to:

- Sika* Method Statement Mixing & Applications of Flooring systems
- Sika® Method Statement Evaluation and Preparation of Surfaces for Flooring systems

IMPORTANT CONSIDERATION

- Do not apply Sikafloor® MultiDur EB-24 on substrates with rising moisture.
- Freshly applied Sikafloor® MultiDur EB-24 must be protected from damp, condensation and water for at least 24 hours.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.
- For exact colour matching, ensure the Sikafloor®-264 in each area is applied from the same control batch numbers.
- Under certain conditions, underfloor heating or high ambient temperatures combined with high point loading, may lead to imprints in the resin.
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

MAINTENANCE

CLEANING

Please refer to the Method Statement Sikafloor®-Cleaning Regime

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must



be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone, Nhon Trach Dist., Dong Nai Province, Vietnam Tel: (84-251) 3560 700 Fax: (84-251) 3560 699 sikavietnam@vn.sika.com





SYSTEM DATA SHEET
Sikafloor® MultiDur EB-24
October 2024, Version 04.01
020811900000000017

SikafloorMultiDurEB-24-en-VN-(10-2024)-4-1.pdf

