

PRODUCT DATA SHEET

Sika® CarboDur® S

Pultruded carbon fibre plates for structural strengthening as part of the Sika® CarboDur® system

DESCRIPTION

Sika® CarboDur® S plates are pultruded carbon fibre reinforced polymer (CFRP) laminates, designed for strengthening concrete, timber, masonry, steel and fibre reinforced polymer structures. The plates are bonded onto the structure as externally bonded reinforcement using Sikadur®-30 epoxy resin based adhesive for normal temperatures, or Sikadur®-30 LP epoxy resin based adhesive for elevated temperatures during application or service. Please refer to the relevant Product Data Sheet for more detailed information about each of these adhesives.

USES

Sika® CarboDur® S may only be used by experienced professionals.

Sika® CarboDur® S is used as a reinforcement plate for externally bonded structural strengthening systems on concrete, masonry, wood, steel and reinforced polymer substrates.

Externally bonded structural strengthening systems are used for:

- Enhancing the load-carrying capacity or ductility of structural members.
- Increasing the flexural loading capacity of elements and structures.
- Improving fatigue resistance.
- Reducing the stress on steel reinforcement.
- Structural upgrading of weak concrete elements or structures.
- Replacing missing steel reinforcement.
- Changing the structural system (removal of floor or wall sections).
- Repairing structural elements after damage (vehicle impact, fire, earthquake).
- Improving impact resistance.
- Passive strengthening for seismic event protection.

Please note:

- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- The Product may only be used by experienced professionals.

CHARACTERISTICS / ADVANTAGES

- Very cost effective in comparison to traditional strengthening techniques.
- Fast application increases productivity, saves time and reduces disruption.
- Improves the service life of a structure.
- Resistant to corrosion.
- Very high strength.
- Excellent durability and fatigue resistance.
- Up to 250 m long, no joints required.
- Easy transport as a roll.
- Low system thickness, simple execution of plate intersections and crossings.
- Low density for minimal additional weight.
- Lightweight, very easy to install, especially overhead (without temporary support).
- Smooth edges without exposed fibres as a result of production by pultrusion.
- Extensive testing and approvals available from many countries worldwide.

APPROVALS / STANDARDS

- European Technical Assessment 21/0276 30/06/2021 EN
- Czech Republic: Technical Approval, ITC, Nr. STO-AO 224-1012/2020/a
- Technical Approval, CSTB, Avis Technique 3.3/20-1021_V1
- Certificate of Technical Valuation, CSLP, Certificate No. 259/2023
- National Technical Assessment Sika CarboDur® kit, ITB, Approval No. ITB-KOT-2018/0414 v.2
- Technical Approval Sika CarboDur, Nr. IBDiM-KOT-2019-0361 v.2
- Technical Agreement, CTPC, No. 016-01/488-2022

- Russia: Technical Certificate Sika® CarboDur®S, No. 6476-22
- Test Report, University of Belgrade, No. 270/2019
- Slovakia: Technical Assessment, TSUS, No. SK04-ZSV-2669
- Technical Approval, DIT, No. N604R/19
- Test Report, Ministry of Regional Development (Ukraine), No. 3HT-219-2167.13-001

PRODUCT INFORMATION

Packaging	Cut to size as follows in non-returnable cardboard packaging. Supplied in rolls of 100 m in non-returnable cardboard boxes.			
Appearance / Colour	Carbon fibre-reinforced polymer with an epoxy matrix, black.			
Shelf life	5 years from date of production			
Storage conditions	Store in original, unopened, sealed and undamaged packaging in dry conditions at temperatures of max. +50 °C. Protect from direct sunlight. Transport only in the original packaging, or otherwise adequately protected against any mechanical damage			
Dimensions	Sika® CarboDur® S	Width	Thickness	Cross section area
	512	50 mm	1.2 mm	60 mm ²
	Kindly contact to Sika for other dimensions.			
Fibre Volume Content	> 68 %			

TECHNICAL INFORMATION

Laminate Tensile Strength	Mean	3100 N/mm ²	(EN 2561)
	5 % characteristic	2900 N/mm ²	
	Mean	3100 N/mm ²	(ASTM D3039)
	Characteristic (ACI 440.2R)	2900 N/mm ²	
Laminate Modulus of Elasticity in Tension	Mean	170 kN/mm ²	(EN 2561)
	5 % characteristic	165 kN/mm ²	
	Mean	165 kN/mm ²	(ASTM D3039)
Laminate Elongation at Break in Tension	Mean	1.80 %	(EN 2561)
Glass Transition Temperature	> +100 °C		

APPLICATION INFORMATION

Consumption	Width of Sika® CarboDur® S plate	Typical consumption of Sikadur®-30
	50 mm	1.00–1.40 kg/m
Consumption rate		
Note: Consumption is for standard application only. Rough or uneven substrate surfaces, plate crossings, loss and wastage can lead to a higher adhesive consumption.		

SYSTEM INFORMATION

System Structure	The system build-up and configuration as described must be fully complied with and may not be changed.	
	Resin adhesive	Sikadur®-30 or Sikadur®-30 LP
	Structural strengthening carbon plates	Sika® CarboDur® S
For detailed information on Sikadur®-30 or Sikadur®-30 LP, together with the resin and plate application details, please refer to the individual Product Data Sheets.		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

SIKA® CARBODUR® PLATES EXTERNALLY BONDED TO THE CONCRETE SURFACE

Recommended minimum concrete pull-off strength after surface preparation:

- Mean: 2.0 N/mm²
- Minimum: 1.5 N/mm²

The effective concrete pull-off strength after surface preparation has to be verified. If concrete pull-off strength is below the stated minimum requirements, alternative Sika solutions are available:

- Sika® CarboDur® applied in slots as near surface mounted (NSM) reinforcement
- SikaWrap® fabrics: Please refer to the Product Data Sheet for the SikaWrap® fabrics

Concrete must generally be older than 28 days (dependent on curing conditions and the type of concrete).

SIKA® CARBODUR® EXTERNALLY BONDED TO OTHER SUBSTRATES

For the application of Sika® CarboDur® plates to all other substrates (brick, stone, steel, wood, fibre reinforced polymer) please refer to Sika Method Statement of Sika® CarboDur® System. Contact Sika Technical Service for detailed advice.

SUBSTRATE PREPARATION

Clean and prepare the concrete to achieve a laitance-free, contaminant-free, open-textured surface.

Refer to Sika Method Statement of Sika® CarboDur® System for further information.

APPLICATION

IMPORTANT

Application by trained personnel

The application of this Product must only be carried out by an applicator that is trained or approved by Sika. The applicator must also be experienced in this type of application.

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

IMPORTANT

Exposure to UV or weathering

The Product is not resistant to permanent UV exposure or weathering. Contact Sika Technical Services for detailed advice.

Maximum service temperature

Note: Maximum permissible continuous service temperature is approximately +50 °C. When using the Sika® CarboHeater 2 for curing Sikadur®-30 LP the maximum continuous service temperature can be increased to +80 °C. Refer to Sika Method Statement of Sika® CarboDur® System and contact Sika Technical Service for detailed advice.

Please refer to the relevant Product Data Sheets and method statement.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



Product Data Sheet

Sika® CarboDur® S

November 2024, Version 07.02

020206010010000040

SikaCarboDurS-en-VN-(11-2024)-7-2.pdf