

PRODUCT DATA SHEET

Sika® ViscoCrete®-3020 PR VN

HIGH RANGE WATER REDUCING CONCRETE ADMIXTURE

DESCRIPTION

Sika® ViscoCrete®-3020 PR VN is a 3rd generation polymer based high performance superplasticizer for producing soft consistency high grade concrete. Sika® ViscoCrete®-3020 PR VN meets the requirements of ASTM C 494 Type G

USES

Sika® ViscoCrete®-3020 PR VN is mainly suitable for the manufacture of concrete for RMC and precast batching plants. Sika® ViscoCrete®-3020 PR VN excels by its extremely high water reduction capacity, providing good flow ability while retaining optimal cohesion of the mix. Sika® ViscoCrete®-3020 PR VN is used for the following types of concrete:

- High-strength / high performance cast on site concrete
- High early strength for concrete shafts
- Bridges and cantilever
- Slender components with dense reinforcement

CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-3020 PR VN combines different modes of actions. By adsorption on the surface of the fines and keeping them apart while the hydration is in progress, Sika® ViscoCrete®-3020 PR VN effects the following concrete properties:

- Extremely high water reduction
- Producing very soft consistency and suitable for long distance pumping
- High flowability (considerably reduced placing and compacting work)
- Workability can be maintained up to 120 minutes (still depends on admixture dosage, cement type, temperature)
- Highly improved waterproofness
- Improved creep and shrinkage resistance characteristics

PRODUCT INFORMATION

Chemical base	Modified Polycarboxylate in water
Packaging	200/1000 litres
Shelf life	12 months if stored properly in original unopened packaging.
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +30 °C
Appearance / Colour	Liquid/ brownish colour
Density	1.090 – 1.110 kg/L (at 20°C)

TECHNICAL INFORMATION

Concreting Guidance

Concrete placing: With the use of Sika® ViscoCrete®-3020 PR VN, concrete of highest quality is being produced, however state of the art concrete technology, such as mixing, placing, vibrating and curing must be respected and applied

Curing: Effective measures for concrete curing must be followed

Specific Advice

Sika® ViscoCrete®-3020 PR VN is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix. For optimum utilization of the high range water reducer we recommend a minimum wet mixing time of 60 seconds.

When adding the balance of the batching water to adjust concrete consistency this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.

APPLICATION INFORMATION

Recommended Dosage

0.7 – 2.5 ltr per 100 kg of cement/binder
Typical 1.1 to 1.6 ltr per 100kg of cement/binder

Compatibility

Sika® ViscoCrete®-3020 PR VN may be combined with all Sikament, Sika® Aer, Sika® Pump, Sikacrete® PP1 products, but must be added separately to the mix and not pre-mixed prior its addition
Sika® ViscoCrete®-3020 PR VN is compatible with all Portland Cement types

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

Protective Measures: Avoid prolonged contact with skin. Wash off thoroughly with soap water.

In case of contact with eyes or mouth, rinse immediately with clean warm water and seek medical attention without delay.

Avoid contact with food stuff and utensils

Ecology/ Waste disposal: Do not dispose of into water or soil, but according to local regulations

Transportation class: Non-hazardous

Toxicity: Non-toxic

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



Product Data Sheet

Sika® ViscoCrete®-3020 PR VN
December 2021, Version 01.02
021301011000004049

SikaViscoCrete-3020PRVN-en-VN-(12-2021)-1-2.pdf

