

## PRODUCT DATA SHEET

# Sika® ViscoCrete®-8125

ULTRA HIGH RANGE WATER REDUCER WITH HARDENING ACCELERATION EFFECT CONCRETE AD-MIXTURE.

### DESCRIPTION

Sika® ViscoCrete®-8125 is a 3rd generation polymer based high performance superplasticizer with hardening acceleration effect for concrete. Sika® ViscoCrete®-8125 meets requirements of ASTM C494 type F.

### USES

Sika® ViscoCrete®-8125 is mainly suitable for the manufacture of concrete in precast factories and other in-situ precast concrete elements.

Sika® ViscoCrete®-8125 is used for the following types of concrete:

- High-strength/High performance concrete spun pile in precast industry.
- Concrete with extreme water reduction.
- Soft consistency concrete with extended working time, suitable for both small and large spun piles.

### CHARACTERISTICS / ADVANTAGES

Sika® ViscoCrete®-8125 combines different modes of actions. By adsorption on the surface of the fines and keeping them apart while the hydration is in progress, Sika® ViscoCrete®-8125 effects the following concrete properties:

- Extremely high water reduction (enhanced impermeability & strength of concrete produced).
- Compatible with SCM like GGBSF, PFA.
- Faster development of early strength. Can reduce the time of steam curing process for getting early strength.
- Workability can be maintained up to 90 minutes (depending on cement type, temperature and mix design).
- Improved creep and shrinkage resistance characteristics.

### PRODUCT INFORMATION

Chemical base	Modified Poly carboxylate in water.
Packaging	200/1000 litres.
Shelf life	12 months if stored properly in original unopened packaging.
Storage conditions	Stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +30 °C.
Appearance / Colour	Liquid/ Brown colour.
Density	1.065 – 1.105 kg/L (20°C).

### TECHNICAL INFORMATION

#### Concreting Guidance

**Concrete placing:** With the use of Sika® ViscoCrete®-8125, concrete of highest quality is being produced, however state of the art concrete technology, such as mixing, placing vibrating and curing must be respected and applied.

## APPLICATION INFORMATION

<b>Recommended Dosage</b>	0.5 – 2.0 ltr per 100 kgs of cement/binder. Typical dosage <ul style="list-style-type: none"><li>▪ For normal concrete 0.6 - 0.9 ltr per 100 kgs of cement/binder.</li><li>▪ For spun pile 0.8 – 1.2 ltr per 100 kgs of cement/binder.</li></ul>
<b>Compatibility</b>	Sika® ViscoCrete®-8125 may be combined with all Sikament, Sika® Aer, Sika® Pump, Sikacrete® PP1 products, but must be added separately to the mix and not pre-mixed prior its addition. Sika® ViscoCrete®-8125 is compatible with all Portland Cement types.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATION

Overdosing will result in increased workability and setting time of the Concrete, however, provided that curing is effective, ultimate concrete strength and properties will not be affected.

Accurate dispensing equipment can be supplied by Sika Limited (Vietnam).

Use an appropriate concrete mixer and do not mix by hand.

Trial mixes are recommended to establish exact dosage rates required to suit individual requirements. Please contact Sika Technical Department for further assistance.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### DISPENSING

Sika® ViscoCrete®-8125 is added to the gauging water prior to its addition to the dry mix or added separately to the wetted concrete mix.

For optimum utilization of the ultra-high range water reducer we recommend a minimum wet mixing time of 60 seconds.

#### Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,  
Nhon Trach Dist., Dong Nai Province,  
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



#### Product Data Sheet

Sika® ViscoCrete®-8125  
September 2024, Version 01.01  
021301011000005872

When adding the balance of the batching water to adjust concrete consistency this should be done after a minimum of 2/3 of the wet mixing time to avoid surplus water in the concrete.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaViscoCrete-8125-en-VN-(09-2024)-1-1.pdf