

PRODUCT DATA SHEET

Sarnafil® TG 76-15 FSA

Polymeric membrane for adhered roof waterproofing

DESCRIPTION

Sarnafil® TG 76-15 FSA is a FPO, multi-layer, self-adhesive, matt finish, weldable sheet membrane with a glass fibre, non-woven reinforcing inlay and polyester fleece backing according to EN 13956. Contains ultraviolet light stabilisers and flame retardants to provide a fast installation, low maintenance and durable membrane.

USES

Sarnafil® TG 76-15 FSA may only be used by experienced professionals.

- Roof waterproofing membrane for exposed flat roofs on smooth substrates

CHARACTERISTICS / ADVANTAGES

- Fast installation
- Instant wind uplift resistance through the self-adhesive backing
- Proven performance over decades
- Resistant to permanent UV exposure
- High dimensional stability from glass fibre inlay
- Resistant against impact load and hail
- Resistant to all common environmental influences
- Resistant to micro-organisms
- Hot air weldable
- No open flame equipment required

PRODUCT INFORMATION

Product Declaration	EN 13956: Polymeric sheets for roof waterproofing
Chemical base	Flexible polyolefins (FPO)
Packaging	Standard rolls are wrapped individually in a blue PE-foil.

SUSTAINABILITY

- Conformity with LEED v4 SSc 5 (Option 1): Heat Island Reduction - Roof (only traffic white)
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- Conformity with LEED v2009 SSc 7.2 (Option 1): Heat Island Effect - Roof (only traffic white)
- Conformity with LEED v2009 MRc 4 (Option 2): Recycled Content

APPROVALS / STANDARDS

- CE Marking and Declaration of Performance to EN 13956 - Polymeric sheets for roof waterproofing

Packing unit	Refer to price list
Roll length	20,00 m
Roll width	2,00 m
Roll weight	80,00 kg

Refer to current price list for packaging variations.

Shelf life	18 months from date of production.	
Storage conditions	Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.	
Appearance / Colour	Surface	matt
	Colours	
	Top surface	beige ~RAL 7040 (window grey) ~RAL 9016 (traffic white)
	Bottom surface	black
Visible Defects	Pass	(EN 1850-2)
Length	20 m (-0 % / +5 %)	(EN 1848-2)
Width	2 m (-0,5 % / +1 %)	(EN 1848-2)
Effective Thickness	1,5 mm (-5 % / +10 %)	(EN 1849-2)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per unit area	2,0 kg/m ² (-5 % / +10 %)	(EN 1849-2)

SYSTEM INFORMATION

System Structure

The following products must be considered for use depending on roof design:

- Sarnafil® T 66-15 D Sheet for detailing
- Sarnafil® T Metal Sheet
- Sarnabar
- Sarnafil® T Welding Cord
- Sarnafil® T Prep / Sarnafil® T Wet Task Set
- Sarnacol® T-660
- Solvent T-660
- Sarnafil® T Clean

Primers:

Substrate	Primer
Sarnatherm PIR GT	Primer-600 / Primer-780
Sarnatherm PIR AL	none
EPS S-Therm ROOF	Primer-780
OSB 3 / Plywood	Primer-600 / Primer-780
Concrete	Primer-600 / Primer-780
Mineral wool (Bondrock MV)	Primer-600 / Primer-780
Metal composite panel	none
Metal (Aluminium, galvanized steel)	none
Bitumen (sanded/slatted)	Primer-600

Ancillary products:

- Prefabricated parts
- Roof drains
- Scuppers

- Walkway pads
- Decor profiles
- Protection sheets

Compatibility	<ul style="list-style-type: none"> ▪ Sarnatherm PIR GT (e.g. Kingspan TR 27) ▪ Sarnatherm PIR AL (e.g. Kingspan TR 26) ▪ EPS DAA ($\geq 20 \text{ kg/m}^3$ density, compressive strength $>100 \text{ kPa}$) ▪ EPS S-Therm PLUS ▪ EPS S-Therm ROOF ▪ OSB 3 / Plywood, Concrete ▪ Mineralwool Bondrock MV ▪ Metal composite panel released by TM Roofing (e.g. Brucha Panel) ▪ Metal (Aluminum, galvanized steel) ▪ Bitumen (sanded/slatted)
----------------------	--

TECHNICAL INFORMATION

Resistance to Impact	hard substrate	$\geq 800 \text{ mm}$	(EN 12691)
	soft substrate	$\geq 1500 \text{ mm}$	
Hail Resistance	rigid substrates	$\geq 25 \text{ m/s}$	(EN 13583)
	flexible substrates	$\geq 40 \text{ m/s}$	
Resistance to Static Load	soft substrate	$\geq 20 \text{ kg}$	(EN 12730)
	rigid substrate	$\geq 20 \text{ kg}$	
Tensile Strength	longitudinal (md) 1)	$\geq 500 \text{ N/50mm}$	(EN 12311-1)
	transversal (cmd) 2)	$\geq 500 \text{ N/50mm}$	
1) md = machine direction, 2) cmd = cross machine direction			
Elongation	longitudinal (md)1)	$\geq 2 \%$	(EN 12311-2)
	transversal (cmd)2)	$\geq 2 \%$	
1) md = machine direction, 2) cmd = cross machine direction			
Joint Peel Resistance	$\geq 300 \text{ N/50 mm}$		(EN 12316-2)
Joint Shear Resistance	$\geq 300 \text{ N/50 mm}$		(EN 12317-2)
Dimensional Stability	longitudinal (md) 1)	$\leq 0,2 \%$	(EN 1107-2)
	transversal (cmd) 2)	$\leq 0,1 \%$	
1) md = machine direction, 2) cmd = cross machine direction			
Foldability at Low Temperature	$\leq -25 \text{ }^\circ\text{C}$		(EN 495-5)
Watertightness	Pass		(EN 1928)
Water Vapour Transmission	$\mu = 150 \text{ 000}$		(EN 1931)
Effect of Liquid Chemicals, Including Water	Resistant to many chemicals. Contact Sika Technical Services for additional information.		
Resistance to UV Exposure	Pass ($> 5000 \text{ h / grade 0}$)		(EN 1297)
External Fire Performance	$B_{\text{ROOF}}(t1) < 20^\circ, > 20^\circ$		(EN 1187) (EN 13501-5)
Reaction to Fire	Class E		(EN ISO 11925-2, classification to EN 13501-5)

APPLICATION INFORMATION

Ambient Air Temperature	5 °C min. / +60 °C max.
Substrate Temperature	5 °C min. / +60 °C max.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTS

Sika[®] Method Statement: Sarnafil[®] TG 76-15 FSA

IMPORTANT CONSIDERATION

Installation work must only be carried out by Sika[®] trained and approved contractors, experienced in this type of application.

- Do not apply to wet, damp or unclean surfaces
- Only apply to compatible materials (refer to compatibility section).
- The use of Sarnafil[®] TG 76-15 FSA membrane is limited to geographical locations with average monthly minimum temperatures of -50 °C. Permanent ambient temperature during use is limited to +50 °C.
- The use of some ancillary products such as adhesives, cleaners and solvents is limited to temperatures above +5 °C. Observe temperature limitations in the appropriate Product Data Sheets.
- Special measures may be compulsory for installation below +5 °C ambient temperature due to safety requirements in accordance with national regulations.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

EQUIPMENT

Hot welding overlap seams

Electric hot air welding equipment, such as hand held manual hot air welding equipment and pressure rollers or automatic hot air welding machines with controlled hot air temperature capability of a minimum +600 °C.

Recommended type of equipment:

- Manual: Leister Triac PID
- Automatic : Sarnamatic 681
- Semi-automatic: Leister Triac Drive

SUBSTRATE QUALITY

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up and the complete roof system must be designed and secured against wind uplift loadings. The substrate must be uniform, firm, solvent resistant, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loose surface sand / gravel dressing.

APPLICATION

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Substrate priming

Prime prepared substrate with appropriate primer

Fixing Method

Sika[®] Method Statement: Fully adhered roof surfaces by integrated self-adhesive film and Sika[®] Method Statement: Sarnafil[®] TG 76-15 FSA

Hot welding overlap seams

Overlap seams must be welded by electric hot welding equipment. Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic conditions prior to welding. The effective width of welded overlaps by hot air must be a minimum 20 mm.

Testing overlap seams

The seams must be mechanically tested with screwdriver or steel needle to ensure the integrity/completion of the weld. Any imperfections must be rectified by hot air welding.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Limited (Vietnam)

Nhon Trach 1 Industrial Zone,
Nhon Trach Dist., Dong Nai Province,
Vietnam

Tel: (84-251) 3560 700

Fax: (84-251) 3560 699

sikavietnam@vn.sika.com



Product Data Sheet

Sarnafil® TG 76-15 FSA

December 2022, Version 03.01

020910052050151001

SarnafilTG76-15FSA-en-VN-(12-2022)-3-1.pdf